

# TECHNICAL DATA SHEET

## THERMOCEM® TC04 “doped” (with magnetic doping)

### Description

ThermoCem® TC04 “doped” is a hydraulically-setting, thermally-optimised dry mortar with increased chemical resistance, developed specially for embedding geothermal probes. This product is magnetically-doped so that the complete filling of the borehole can be verified by measurement technologies using the magnetic susceptibility.

### Formulation

		per m <sup>3</sup> of suspension	per bag
ThermoCem® TC04 „doped”	[kg]	1063	25
Water	[liter]	637	15
Yield	[liter]	1000	24

### Data

		Laboratory data <sup>1)</sup>	Value range job-site <sup>2)</sup>
Suspension temperature	[°C]	20	≥ 5
Suspension density	[kg/l]	1.70	≥ 1.67
Flow channel	[s]	50 - 80	≥ 50
Marsh viscosity	[cm]	≥ 50	≥ 50
Water separation	after 1 hour	[%]	1.0
	after 24 hours	[%]	2.0
Compressive strength <sup>3)</sup>	after 7 d	[MPa]	9.0
	after 28 d	[MPa]	15.0
Thermal conductivity	[W/mK]	4.0	
Permeability coefficient <sup>4)</sup> (k-value)	[m/s]		< 1 x 10 <sup>-10</sup>
Processing time	[h]		2

<sup>1)</sup> Guidelines for the preconstruction test in accordance with LQS EWS Baden-Württemberg (December 2018)

<sup>2)</sup> Permissible range of value for testing at job-site in accordance with LQS EWS Baden-Württemberg (December 2018)

<sup>3)</sup> Compressive strength in accordance with DIN EN 196 (prisms)

<sup>4)</sup> Permeability coefficient in accordance with DIN EN 17892-11

#### Mixing procedure laboratory

- Bucket 5 litre
- Volume of suspension 3 litres (water-solid-ratio = 0.6)
- Colour mixer ∅ 100 mm
- Mixer speed 1.200 rpm, mixing time 120 seconds

#### Status: March 2024

Page 1 of 2

The above data relate to tests under laboratory conditions with the usual metrological tolerances. These along with records of other “suitability tests” are designed to obtain information about the basic suitability of our product in respect of the intended purpose. Even in the case of a project-specific test, the information should not be regarded as a promise of properties with the effect that we can be held responsible for damages resulting from the absence of features and/or properties. Our information therefore does not release customers from the obligation to carry out their own specific tests and take decisions on their own responsibility.

#### Heidelberg Materials AG

Zur Anneliese 7  
59320 Ennigerloh  
Germany  
Telefon +49 2524 29-51700  
Telefax +49 2524 29-51715



## THERMOCEM® TC04 “*doped*” (with magnetic doping)

---

### Chemical resistance

ThermoCem® TC04 “*doped*” has a high chemical resistance to water and soil with increased content of sulfate and lime-dissolving carbonic dioxide. This is verified by practical performance tests. Individual case assessments are to be done with project specific analyses taking into account DIN EN 206 or DIN 4030-1.

### Freeze-Thaw resistance

ThermoCem® TC04 “*doped*” has a high freeze-thaw resistance. This is verified by internal procedures (referring to Austrian standard B 3303).

### Processing

A flowable ThermoCem® TC04 “*doped*” suspension is to be prepared by adding the receptive amount of water (drinking water quality). The mixer, the mixing intensity and mixing time have to be chosen to meet the desired values for the job-site given in this data sheet. The suspension has to be lump-free and homogeneous.

To minimize suspension loss in the borehole, you can reduce the shore of water, prolong the mixing time and increase the mixing intensity.

In so doing the flowability, water loss and yield point can be influenced positively.

The processing time at a suspension temperature of 20 °C is up to 2 hours. Varying ambient conditions and mixing parameters can lead to different processing times.

The filling of the bore-hole is to be done by the tremie method (from bottom to top) to get a void-free backfilling.

Further information can also be downloaded from [www.heidelbergmaterials.de](http://www.heidelbergmaterials.de)

### Delivery and storage

25 kg bags on Euro pallet, shrunk all around; Silo or big bag. Dry storage on pallets is required. When properly stored, the material can be kept for at least 6 months.

**Status: March 2024**

Page 2 of 2

The above data relate to tests under laboratory conditions with the usual metrological tolerances. These along with records of other “suitability tests” are designed to obtain information about the basic suitability of our product in respect of the intended purpose. Even in the case of a project-specific test, the information should not be regarded as a promise of properties with the effect that we can be held responsible for damages resulting from the absence of features and/or properties. Our information therefore does not release customers from the obligation to carry out their own specific tests and take decisions on their own responsibility.

### Heidelberg Materials AG

Zur Anneliese 7  
59320 Ennigerloh  
Germany  
Telefon +49 2524 29-51700  
Telefax +49 2524 29-51715

